

Express Mail No.: **EL073777538US**Date: **February 18, 2000**

I hereby certify that this correspondence is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Commissioner of Patents and Trademarks, Washington, D.C. 20231.

ANTONELLA FUSILLO

(Name of person mailing paper or fee)

(Signature)

09/486021
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371

 Attorney's Docket No:
BECKER-5

INTERNATIONAL APPLICATION NO.

PCT/DE98/02449

INTERNATIONAL FILING DATE

August 21, 1998

PRIORITY DATE CLAIMED

August 21, 1997**February 27, 1998****March 2, 1998**

TITLE OF INVENTION

VERFAHREN ZUM SPRITZGIESSEN, SPRITZGIESSFORM UND SPRITZGIESSVORRICHTUNG SOWIE VERFAHREN ZUM BEFÜLLEN EINES HAUPTEXTRUDERS AUS EINEM NEBENEXTRUDER

APPLICANT(S) FOR DO/EO/US

HEINER BECKER

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☐ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☐ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US)
6. ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ Original or facsimile of an oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. concern other document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☐ A **FIRST** preliminary amendment.
☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☐ Other items or information:

U.S. APPLICATION NO. (if known, see 37 CFR 1.5)		INTERNATIONAL APPLICATION NO.	ATTORNEY'S DOCKET NO.
09/486021		PCT/DE98/02449	BECKER-5

17. ☒ The following fees are submitted :
 BASIC NATIONAL FEE (37 C.F.R. 1.492(a)(1)-(5):

<input checked="" type="checkbox"/> For filing with EPO or JPO search report (37 C.F.R. 1.492(a)(5))	\$ 840.00	\$840.00
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 C.F.R. 1.492(a)(1))	\$ 670.00	
<input type="checkbox"/> No international preliminary examination fee paid to USPTO (37 C.F.R. 1.492(a)(2)) but international search fee paid to USPTO (37 C.F.R. 1.445(a)(2))	\$ 760.00	
<input type="checkbox"/> Neither international preliminary examination fee paid to USPTO (37 C.F.R. 1.492(a)(3)) nor international search fee paid to USPTO (37 C.F.R. 1.445(a)(2))	\$ 970.00	
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 C.F.R. 1.492(a)(4)) and all claims satisfied provisions of PCT Articles 33(2)-33(4)	\$ 96.00	

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492(e)).

Claims	Number Field	Rate
Total Claims	27-20	x \$ 18.00
Independent Claims	-3	x \$ 78.00
Multiple dependent claims (if applicable)		x \$260.00
TOTAL OF ABOVE CALCULATIONS		\$840.00

Reduction by 1/2 for filing by small entity, if applicable. Verified small entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28)

SUBTOTAL \$840.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date 37 CFR 1.492(f).

TOTAL NATIONAL FEE \$840.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +

\$ 0.00

TOTAL FEES ENCLOSED \$840.00

Amount to be refunded charged

a. ☒ A check in the amount of **\$840.00** to cover the above fees is enclosed.


b. ☐ Please charge my Deposit Account No. **06-0502** in the amount of \$ _____ to cover the above fees. A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. **06-0502**. A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

Send all correspondence to:

HENRY M. FEIEREISEN
 350 Fifth Avenue
 Suite 3220
 New York, N.Y. 10118
 (212) 244-5500
 Date: February 18, 2000



 HENRY M. FEIEREISEN
 Registration No. 31,084

VERIFICATION OF A TRANSLATION

I, Antonella Fusillo, resident of the United States, residing at 28-32 45th Street,
2F, Astoria, N.Y. 11103, depose and state that:

1. I am familiar with the English and German languages.
2. I have read the attached German Search report regarding German patent application no. 198 08 145.6.
3. The hereto attached English language text is an accurate translation thereof.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.



Antonella Fusillo

Date: May 17, 2000

Applicant or Patentee: HEINER BECKER Attorney's Docket No.: BECKER-5
 Serial or Patent No.: _____ Filed or Issued: _____
 For: VERFAHREN ZUM SPRITZGIESSEN, SPRITZGIESSFORM UND SPRITZGIESSVORRICHTUNG SOWIE
VERFAHREN ZUM BEFÜLLEN EINES HAUPTEXTRUDERS AUS EINEM NEBENEXTRUDER

VERIFIED STATEMENT (DECLARATION CLAIMING SMALL ENTITY STATUS (37 CFR 1.9(f) and 1.27(b) SMALL BUSINESS CONCERN

I hereby declare that I am

- ☐ the owner of the small business concern identified below:
☐ an official of the small business concern empowered to act on behalf of the concern identified below:

NAME OF CONCERN: STRUCTOFORM SPRITZGIESSEN ANISOTROPER STRUKTURKOMPONENTEN GMBH
 ADDRESS OF CONCERN: Jülicher Strasse 336
52070 Aachen / Germany

I hereby declare that the above identified small business concern qualifies as a small business concern as defined in 13 CFR 121.3-18, and reproduced in 37 CFR 1.9(d), for purposes of paying reduced fees under section 41(a) and (b) of Title 35, United States Code, in that the number of employees of the concern, including those of its affiliates, does not exceed 500 persons. For purposes of this statement, (1) the number of employees of the business concern is the average over the previous fiscal year of the concern of the persons employed on a full-time, part-time or temporary basis during each of the pay periods of the fiscal year, and (2) concerns are affiliates of each other when either, directly or indirectly, one concern controls or has the power to control the other, or a third party or parties controls or has the power to control both. I hereby declare that rights under contract or law have been conveyed to and remain with the small business concern identified above with regard to the invention, entitled VERFAHREN ZUM SPRITZGIESSEN, SPRITZGIESSFORM UND SPRITZGIESSVORRICHTUNG SOWIE VERFAHREN ZUM BEFÜLLEN EINES HAUPTEXTRUDERS AUS EINEM NEBENEXTRUDER, by inventor(s) HEINER BECKER as described in

☒ the specification filed herewith
 application serial no. _____ filed : _____
 patent no. _____ issued : _____

If the rights held by the above identified small business concern are not exclusive, each individual, concern or organization having rights to the invention is listed below and no rights to the invention are held by any person, other than the inventor, who could not qualify as a small business concern under 37 CFR 1.9(d) or by any concern which would not qualify as a small business concern under 37 CFR 1.9(d) or any nonprofit organization under 37 CFR 1.9(e). * NOTE: Separate verified statements are required from each named person, concern or organization having rights to the invention averring to their status as small entities. (37 CFR 1.27)

FULL NAME: _____
 ADDRESS: _____
☐ Individual ☐ Small Business Concern ☐ Nonprofit Org.
 FULL NAME: _____
 ADDRESS: _____
☐ Individual ☐ Small Business Concern ☐ Nonprofit Org.

I acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement to small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37CFR 1.28(b)).

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application, any patent issuing thereon, or any patent to which this verified statement is directed.

NAME OF PERSON SIGNING: Heiner Becker

TITLE OF PERSON OTHER THAN OWNER: _____

ADDRESS OF PERSON SIGNING: Redmontstraße 34, D-52064 Aachen, Germany

SIGNATURE Heiner Becker Date 15.03.2000

Jülicher Strasse 336

52070 Aachen

PATENT


PTO: 07/10/2001 10 MAY 2000
IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Docket No.: BECKER-5

In re Application of:)
HEINER BECKER)
Appl. No: 09/486,021)
Filed: February 18, 2000)
For: PROCESS FOR INJECTION MOLDING, INJECTION)
MOLD AND INJECTION MOLDING DEVICE, AS)
WELL AS PROCESS FOR FILLING A MAIN)
EXTRUDER FROM A SECONDARY EXTRUDER))

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail in an envelope addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231, on <u>May 17, 2000.</u>	
(Date)	
Henry M. Feiereisen	
(Name of Registered Representative)	
	5/17/2000
Signature	Date of Signature

S I R:

Preliminary to the first Official Action in the above-entitled application,
please amend the application as follows:

IN THE SPECIFICATION:

Change the title to read: --PROCESS FOR INJECTION MOLDING, INJECTION MOLD AND INJECTION MOLDING DEVICE, AS WELL AS PROCESS FOR FILLING A MAIN EXTRUDER FROM A SECONDARY EXTRUDER--.

Page 1, line 4, add the heading --BACKGROUND OF THE INVENTION--.

Page 2, line 6, add the heading --SUMMARY OF THE INVENTION--.

Page 15, line 17, add the heading --BRIEF DESCRIPTION OF THE DRAWING--.

Page 18, line 20, add the heading --DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS--.

Page 35, after the heading "CLAIMS" and before the first claim add --What is claimed is:--.

IN THE CLAIMS:

Cancel claim 2 without prejudice.

Amend the following claims:

1. (Amended) [Process] A process for injection molding of injection molded parts from plasticizeable material, [including] comprising the steps of injecting a first plasticized material into the hollow of an injection mold through an opening [and subsequently injecting another plasticized material into the hollow, characterized in that the first plasticized material is so introduced into the hollow] as to wet only a partial area of [the] a wall surface of the hollow, and [that] subsequently injecting [the other] a second plasticized material [is so introduced] through the same opening into the hollow as to wet at least a part of the remaining area of the wall surface of the hollow.

3. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein the first material is injected into the injection mold to such an extent that after injection of the other material, the first material extends to a shoulder in the hollow between the partial area and the remaining area.
4. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein after injection of the first material, a slide gate is moved to clear at least a part of the remaining area.
5. (Amended) [Process] The process of [according to] claim 4[, characterized in that] wherein the slide gate clears a channel leading to a partial area of the hollow in the injection mold.
6. (Amended) [Process] The process of [according to] claim 4[, characterized in that] wherein the slide gate directly clears a partial area of the hollow in the injection mold.

7. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein during the injection molding [operation] steps a gas space is formed in the injection mold.
8. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein one of the first and second plasticized [material] materials is a relatively soft or rubber-like material, and [at least one] the other one of the first and second plasticized [material] materials is a relatively hard material.
9. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein the first and second plasticized materials exhibit at least two different colors or are transparent.
10. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein at least one of the first and second plasticized [material] materials contains gas pockets.
11. (Amended) [Process] The process [according to one of the preceding claims, characterized in that] of claim 1 wherein at least one of the first and second plasticized [material] materials contains pockets of another component.

12. (Amended) [Injection] An injection mold, [characterized in that it comprises] comprising a body member having a wall surface bounding a hollow for so receiving a first plasticized material as to wet only a partial area of the wall surface of the hollow, and subsequently so receiving a second plasticized material as to wet at least a part of the remaining area of the wall surface of the hollow; and a sensor arranged at [the] a transition between the partial area and the remaining area of the wall surface of the hollow [in the injection mold] of the body member.
13. (Amended) [Injection] The injection mold[, in particular according to] of claim 12[, characterized in that it comprises] wherein the body member is formed interiorly with a shoulder arranged at the transition between the partial area and the remaining area of the wall surface of the hollow [in the injection mold].
14. (Amended) [Injection] The injection mold[, in particular according to] of claim 12 [or 13, characterized in that it comprises], and further comprising a hot runner with a by-pass device which enables plasticized material, streaming to the hollow, to flow into an overflow.
15. (Amended) [Injection] An injection molding device with a plasticizer unit and an injection unit, [characterized in that it comprises] comprising at least two secondary extruders which are arranged between screw tip and nozzle tip.

16. (Amended) [Injection] An injection molding device having at least one injection unit which includes an injection piston (201) for injecting melt from a melt compartment, and at least two extruders (203, 204) connected to this melt compartment.
17. (Amended) [Injection] An injection molding device having a main extruder (237, 257) which includes a melt compartment from which a nozzle extends via a hot runner (241), and a secondary extruder (236, 258), [characterized in that] wherein the melt compartment is connected via a control [device] unit (230, 240) to a second channel which is connected with the secondary extruder (236, 258) and leads to the melt compartment, with the control device being coupled with the movement of the secondary extruder.
18. (Amended) [Injection] The injection molding device [according to] of claim 17, [characterized in that] wherein the control unit (230, 240) is rigidly connected with the secondary extruder (236).
19. (Amended) [Injection] The injection molding device [according to] of claim 17 [or 18], [characterized in that] wherein the control unit (230) includes an adjustment nozzle which bears upon a surface, preferably of a secondary extruder, and is secured to a flange.

20. (Amended) [Injection] The injection molding device molding device [according to one of the claims] of claim 17 [to 19], [characterized in that] wherein the hot runner (241) includes a pressure-dependent valve (245).
21. (Amended) [Injection] The injection molding device molding device [according to one of the claims] of claim 17 [to 20], [characterized in that] wherein the control unit (230, 240) includes two partial channels (234, 235; 241, 242, 243) which, depending on the position of the control unit, open or close the hot runner or a feed channel from the secondary extruder.
22. (Amended) [Injection] The injection molding device [according to] of claim 21, [characterized in that] wherein the control unit (230) includes a partial runner block (231) which accommodates the partial channels (234, 235) and is guided in a block guide (233).
23. (Amended) [Injection] An injection molding device comprising a main extruder (257) movable along a path between an injection position and an idle position, and a secondary extruder (258), [characterized by] and a control unit (250) which is arranged between the injection position and the idle position and includes a channel (253) with an inlet (251) and an outlet (252) and which is swingable between a charging position and release position, wherein the inlet (251) points to the main extruder (257) in the charging position, and the outlet (252) points to the main extruder (257), and wherein the path is cleared for the main extruder (257) in the release position.

24. (Amended) [Injection] The injection molding device [according to] of claim 23, [characterized in that] wherein the inlet (251) and the outlet (252) define an acute angle relative to one another.
25. (Amended) [Injection] An injection molding device comprising a main extruder movable along a path between an injection position and an idle position, and having a nozzle (301) for projecting in its injection position through a nozzle plate (302) and at least a portion of an adapter plate (303) through an injection opening (304), and a secondary extruder which is shiftable between a charging position and a release position, wherein in the release position the path of the main extruder is cleared and in the charging position an outlet (307) of the secondary extruder points to the nozzle (301) of the main extruder, characterized in that the outlet (307) is arranged in an opening (305) of the adapter plate (303) which terminates in the injection opening (304).
26. (Amended) [Injection] The injection molding device [according to] of claim 25, [characterized in that] wherein the secondary extruder is supported on its side of the outlet, at least in its charging position, by a force applied by the main extruder.

27. (Amended) [Method] A method of charging a main extruder of an injection molding device with a melt from a secondary extruder, comprising filling the melt into the main extruder via a feed channel in a hot runner which, on the one hand, is connected with the main extruder and, on the other hand, leads to a mold, and so controlling the injection process that in the hot runner between mold and the location at which the feed channel terminates in the hot runner, a sprue of a solidified or solidifying workpiece remains, until the main extruder is filled with melt.

Add the following claims:

28. (New) The process of claim 1 wherein the opening is formed in a nozzle of an extruder operatively connected to the injection mold.

REMARKS

This Amendment is submitted preliminary to the issuance of an Office Action in the present application.

Applicant has amended claims 1, 3 to 27 to present them in better form for examination. Claim 2 has been canceled. A check in the amount of \$184.00 to cover the surcharge for presenting eight claims in excess of twenty and five claims independent claims in excess of three is enclosed. In addition, applicant has amended the specification to present it with proper headings.

When the Examiner takes this application up for action, he is requested to take the foregoing into account.

The Commissioner is hereby authorized to charge fees which may be required, or credit any overpayment to Deposit Account No. 06-0502.

Respectfully submitted,

By: 

Henry M. Feiereisen
Agent for Applicant
Reg. No. 31,084

Date: May 17, 2000
350 Fifth Avenue
Suite 3220
New York, N.Y. 10118
(212) 244-5500
HMF:af

12 ppts

09/486 021

10 MAY 2000

1 PROCESS FOR INJECTION MOLDING, INJECTION MOLD AND INJECTION
2 MOLDING DEVICE, AS WELL AS PROCESS FOR FILLING A MAIN
3 EXTRUDER FROM A SECONDARY EXTRUDER

4
5 The invention relates to a process for injection molding of injection molded
6 parts from plasticizeable material, wherein a first plasticizeable material is
7 injected into the hollow of an injection mold, and subsequently another
8 plasticized material is injected into the hollow, as well as to an injection mold and
9 an injection molding device with a plasticizer unit and an injection unit.

10
11 Processes of this type are known under the term "mono-sandwich
12 process" and "two-component process".

13
14 The mono-sandwich process includes initially injecting into an injection
15 mold, for example, a particularly pure plasticized material which hardens on the
16 wall surface of the injection mold, and subsequently injecting a filler which forms
17 the core of the injection molded part and generally contains inferior materials.
18 This makes it possible, at low materials costs, in particular when using recycled
19 materials, to produce injection molded parts with surfaces that are formed
20 entirely from high-grade materials.

21
22 In order to produce injection molded parts with elements of various
23 materials, the two-component process is used which includes various injection

1 units for introducing plasticizeable materials into the injection mold at various
2 locations, so that, for example, a toothbrush can be made with areas of hard
3 plastic and a flexible intermediate area of softer plastic. The two-component
4 process requires, however, a very complicated injection molding device so that
5 the production process becomes relatively expensive.

6
7 In view of the known prior art, it is an object of the invention to propose a
8 simple injection molding process for making injection molded parts from various
9 materials.

10
11 This object is attained in accordance with a generic process by so
12 introducing a first plasticized material into the hollow as to wet only a partial area
13 of the wall surface of the hollow, and by subsequently so introducing another
14 plasticized material into the hollow as to wet at least a part of the remaining area
15 of the wall surface of the hollow.

16
17 According to the process of the invention, part of the hollow is kept initially
18 inaccessible, or such a small quantity of the first plasticizeable material is
19 injected that only part of the wall surface of the hollow is wetted. Subsequently at
20 least one further material is introduced into the then cleared remaining hollow to
21 harden in the remaining area of the wall surface of the hollow, so that the finished
22 injection molded part comprises an exterior surface made of various materials.

1 The process allows the use of a modified conventional mono-sandwich
2 injection molding machine, whereby, in contrast to current conventional
3 processes, particular regard is directed to the fact that the second material is not
4 completely enveloped by the first material. In particular, when the second
5 material is also a high-grade material, the process according to the invention
6 permits the production of injection molded parts from various materials which
7 cannot be distinguished from conventional injection molded parts made by the
8 two-component process.

9
10 According to a preferred variation, the first plasticized material and at least
11 one other plasticized material are injected into the hollow through the same
12 opening. A single opening in the injection mold for various materials results in
13 lower production costs for the injection molding device and permits a simple
14 process control as the individual materials are injected in succession into the
15 injection mold at the same location. Exact dosage and filling times realize
16 outstanding production results at most different injection molded parts.

17
18 Since the transition area of the injection molded part between the partial
19 area and the remaining area of the wall surface oftentimes forms in practice an
20 irregular or blurred line, it is proposed to introduce only so much first material into
21 the injection mold that after injection of the other material, the first material
22 extends up to a shoulder in the hollow between the partial area and the
23 remaining area. The shoulder may be a random edge which preferably projects

1 from the wall surface into the interior of the hollow and forms a barrier against
2 continuous flow of the first plasticized material into the area of the shoulder.

3
4 As an alternative, or in addition to, the described process, after injection of
5 the first material a slide gate can be moved to clear at least part of the remaining
6 area. The term "slide gate" will refer to either a valve-like element which clears a
7 channel to a partial area of the hollow in the injection mold. This allows directing
8 the flow of the plasticized material from a single injection point via various
9 channels into various partial areas of the hollow. However, the slide gate can
10 also be designed as a plunger which, when pushed into a partial area of the
11 hollow in the injection mold, covers a partial area of the wall surface of the
12 hollow. When the slide gate is retracted, at least part of the remaining area of the
13 wall surface of the hollow is cleared, so that the other plasticized material wets
14 the wall surface of the hollow in this area.

15
16 Beyond the use of various plasticizeable materials, hollow injection
17 molded parts can also be produced when a gas space is formed in the injection
18 mold during the injection molding process. Such a gas space is realized by
19 injecting a gas during the injection molding process. Cavities may also be formed
20 in a way that a material quantity is stretched into an empty space of the hollow
21 (injection blow molding) to thereby allow cost-efficient production of
22 two-component injection blow molded parts which contain a hollow. The hollow
23 may remain under constant gas pressure.

1 A great number of particularly advantageous applications can be
2 implemented when one plasticized material is a relatively soft or rubber-like
3 material, and at least one other plasticized material is a relatively hard material.
4 Whereas the soft or rubber-like material can assume the function of a seal, a tire
5 or a handle, the relatively hard material serves for the creation of a solid base
6 body.

7
8 Particular effects can also be realized when the plasticizeable materials
9 exhibit at least two different colors or are transparent. While the various colors
10 create optical effects, it is also possible to produce injection molded parts with
11 colored and transparent areas which for example can be used as a cover with a
12 transparent window. In particular, transparent injection molded parts, which are
13 dyed in partial areas to avoid transparency, can be realized by the described
14 process in a particularly cost-efficient manner.

15
16 In addition, it is advantageous for various applications when at least one
17 plasticized material includes gas pockets. Gas pockets reduce weight and
18 material use and may offer other specific advantages, depending on the purpose
19 of use.

20
21 For example, to use recycling particles, it is proposed that at least one
22 plasticized material includes pockets of another component. Thus, it is possible
23 to admix, for example, elastomeric recycling particles to a soft material, to adjust

1 the hardness of the material.

2
3 The above-described process is also capable to combine a biodegradable
4 material with other materials, in particular with other biodegradable materials. In
5 this case, a material mixture can be realized, on the one hand, and the various
6 materials can be injected also as first and second materials, on the other hand.
7 This combination opens up completely new options as the biodegradable
8 material can be enveloped, for example, by a protective layer. In particular, this
9 protective layer can be made resistant over a period or under certain
10 circumstances. For example, material that can be degraded by water may be
11 enveloped by a layer that can be degraded by microorganisms or by UV light,
12 thereby realizing a water-resistant part which still can be degraded rapidly after
13 degrading the outer layer. It will be understood that the combination of a
14 biodegradable material is advantageous per se.

15
16 Especially suitable for carrying out the process according to the invention
17 is an injection mold which has at least one sensor disposed at the transition
18 between the partial area and the remaining area of the wall surface of the hollow
19 in the injection mold. Such sensors permit, for example by means of pressure
20 gauges, temperature gauges or ultrasound measuring devices, to ascertain when
21 a particular plasticized material reaches the location on the wall surface where
22 the sensor is located. In this manner, the injection process can be accurately
23 monitored and controlled.

1 In particular, it is possible to arrange such a sensor in an ejection bore of
2 the mold. For example, the sensor may be an ultrasonic sensor for use as quality
3 assurance. By utilizing an ejection bore, the sensor can easily be attached
4 because suitable ejection bores are provided anyway and the provision of only a
5 further respective bore is required. Also, an existing bore, in particular when
6 existing molds are involved, can be used.

7
8 It will be understood that any kind of bore may be referred to in the
9 ejection block so long as it reaches the workpiece. The bore may be closed on
10 the side of the mold. Still it is possible to very easily position a sensor in
11 immediate proximity of the workpiece by means of this bore.

12
13 It is advantageous to provide an injection molding device, which is
14 especially useful for the process according to the invention, with a shoulder at the
15 transition between the partial area and the remaining area of the wall surface of
16 the hollow in the injection mold. This shoulder, permits, as stated above, to
17 create a straight transition line between the components.

18
19 During hot-runner injection molding, a two-component mixture remains in
20 the hot runner of the injection mold and may reach during injection of a further
21 part, the hollow of the injection mold. This would, however, lead to a
22 contamination of the outer layer of the next injection molded part. It is therefore
23 proposed that the injection mold includes a hot runner with a by-pass device

1 which permits plasticized material that flows to the hollow to flow into an
2 overflow. After the first injection molding operation, the by-pass device diverts
3 oncoming material into the overflow until pure material reaches the runner. Thus,
4 contaminations can be collected in the overflow for subsequent disposal. Material
5 collected in the overflow may also further be utilized, for example, to
6 subsequently purposely seal a gas hole in proximity of the overflow. This may be
7 implemented by a plunger which conveys melt from the overflow.

8
9 Also proposed is an injection molding device with a plasticizer unit and an
10 injection unit, which includes at least two secondary extruders arranged between
11 screw tip and nozzle tip. The use of several secondary extruders permits
12 sequential introduction of various materials into the injection mold to produce
13 injection molded parts from most different materials by using the process
14 according to the invention.

15
16 In addition, an injection molding device is proposed which includes at least
17 one injection unit having an injection piston by which melt is injected from a melt
18 compartment, and at least two extruders connected to this melt compartment.
19 Such an arrangement is capable to injection-mold extremely small workpieces
20 and to use thereby also very sensitive melts. In particular, it is possible, to charge
21 the melt compartment with two different melts according to the FIFO (first in, first
22 out) principle, and to produce in this manner precision components from various
23 materials or to execute micro injection molding with two different materials.

1 An injection molding device including a main extruder, which includes a
2 melt compartment from which a nozzle extends via a hot runner, and a
3 secondary extruder can be operated in an especially simple manner by
4 transferring melt from the secondary extruder from the melt compartment, when
5 a second channel, connected to the secondary extruder, is added to the melt
6 compartment via a control unit which is coupled with the movement of the
7 secondary extruder.

8
9 Such a coupling may be implemented, for example in a simple manner, by
10 a rigid connection between control device and secondary extruder. On the other
11 hand, spring elements may be provided. Moreover, it is also conceivable to
12 actively operate the control device through control via a pneumatic or hydraulic
13 mechanism in dependence on the movement of the plasticizer unit.

14
15 The control unit may include an adjustment nozzle which bears upon a
16 surface, preferably a surface of the secondary extruder, and is secured with a
17 flange. Such an adjustment nozzle ensures, regardless of other features of the
18 injection molding device, an extremely simple construction and an extremely
19 simple replacement of the adjustment nozzle.

20
21 It is also secondary to what extent this nozzle has incorporated therein hot
22 runners or only feed channels.

1 Furthermore, the hot runner may include a pressure-dependent valve. In
2 such an arrangement, the flow conduction control of the hot runner via the
3 movement of the secondary extruder may be omitted. Flow conduction is then
4 controlled pressure-dependent. When melt is transferred from the secondary
5 extruder to the main extruder at low pressure, such a pressure valve will not yet
6 respond. Only when the pressure reaches the level during injection molding
7 through the main extruder will the valve respond. In this manner, the injection
8 molding process can further be simplified. Such a pressure-dependent valve is
9 also useable in an advantageous manner, regardless of the remaining features of
10 the injection molding device.

11
12 The control unit may, on the other hand, include two partial channels
13 which open or close the hot runner or feed channel depending on the position of
14 the control unit. In this manner, a simple control of the control unit is realized in
15 dependence on the movement of the secondary extruder.

16
17 In particular, it is possible to so construct one of the partial channels that it
18 closes the second channel from the secondary extruder to the main extruder
19 when the secondary extruder has reached its transport position to convey melt to
20 the main extruder.

21
22 The control unit may include a partial channel block which accommodates
23 the partial channels and is guided in a block guide, thereby ensuring a reliable

1 flow control. For example, the above-described adjustment nozzle may be
2 conceivable as partial channel block. Also other devices, such as plates having
3 partial channels are conceivable as partial channel block. The partial channel
4 block may, as described above, be connected with the secondary extruder or
5 activated independently therefrom.

6
7 A particular simple construction can be implemented when the block guide
8 accommodates a hot runner. In this manner, the partial channel block may then
9 be so shifted that, on the one hand, one partial channel opens the hot runner
10 and, on the other hand, the other partial channel - when the partial channel block
11 occupies the respective position - opens the pathway between secondary
12 extruder and hot runner or main extruder.

13
14 Furthermore, an injection molding device is proposed which includes a
15 main extruder, movable between an injection position and an idle position along
16 a path, and at least one secondary extruder which includes a control unit,
17 disposed between the injection position and the idle position, with the control unit
18 including a channel with an inlet and an outlet and swingable between a charging
19 position and a release position, wherein in the charging position the inlet points to
20 the secondary extruder and the outlet points to the main extruder, and wherein in
21 the release position the pathway for the main extruder is cleared. When rigidly
22 connecting the inlet with the secondary extruder, the above-stated coupled

1 movement between control unit and secondary extruder is carried out directly.
2 However, other linkages are certainly also conceivable.

3
4 Such a swingable control unit is capable to significantly accelerate and
5 facilitate the process cycle of the above-described process as well as of other
6 processes, also regardless of the coupled movement with the secondary
7 extruder, as a conjoint movement of the secondary extruder or extruders with the
8 main extruder is no longer required. Rather, the secondary extruders as well as
9 the control unit are appropriately controlled in dependence on the respective
10 process stage. When the main extruder is in its idle position, the control unit
11 occupies its charging position, and the secondary extruder and the main extruder
12 are connected to the inlet and outlet, respectively, of the control unit. The main
13 extruder can then be charged by the secondary extruder. After charging, the
14 secondary extruder is removed from the inlet and the control unit is swung away
15 to clear the path for the main extruder.

16
17 The above-described arrangement is very compact when the inlet and the
18 outlet of the control unit define an acute angle relative to one another. Such an
19 arrangement permits disposition of the control unit immediately in front of a
20 nozzle plate of the injection molding device, as no additional space is required in
21 this location for the secondary extruder which projects approximately in a
22 V-shaped manner from the main extruder. In this way, the pathway to be traveled

1 by the main extruder can be minimized so that the overall time for the injection
2 molding process can be reduced.

3
4 It will be understood that such a V-shaped disposition of main extruder
5 and secondary extruder is already advantageous to reduce the required
6 structural space and thus the pathway to be traveled by the main extruder.

7
8 Furthermore, an injection molding device is proposed including a main
9 extruder movable between an injection position and an idle position along a path
10 and traversing with a nozzle in its injection position a nozzle plate and at least a
11 portion of an adapter plate through an injection opening, and a secondary
12 extruder which is displaceable between a charging position and a release
13 position, whereby the path of the injection device is cleared in the release
14 position and an outlet of the secondary extruder points in the charging position to
15 the nozzle of the main extruder, with this outlet being disposed in an opening of
16 the adapter plate which terminates in the injection opening. The opening of the
17 adapter plate may terminate in the injection opening at an angle of 90° , on the
18 one hand, or also at an acute angle, on the other hand.

19
20 It is also conceivable, to provide the opening for the secondary extruder in
21 the nozzle plate. In particular when the adapter plate is absent is this of
22 advantage, whereby the outlet of the secondary extruder is arranged in the

1 charging position in an opening of the nozzle plate which is aligned with the
2 injection opening.

3
4 Through the above-described measure, the position which the main
5 extruder should occupy when being filled with melt by the secondary extruder,
6 can be shifted to a location immediately proximate of the mold, up into the mold
7 space. In this manner, the pathway to be traveled by the main extruder is
8 minimized when being retracted for clearing the outlet, so that the overall time for
9 the injection process is reduced.

10
11 The secondary extruder may be supported on the outlet side at least in its
12 charging position by a force applied by the main extruder. This may implemented
13 by a guide in the adapter plate or by a lug engaging the adapter plate. In this
14 way, a correct seat of the main extruder upon the outlet of the secondary
15 extruder is ensured during charging of the main extruder from the secondary
16 extruder. Furthermore, there is no need to construct the secondary extruder in a
17 particularly stable fashion as the above-described support provides for a
18 sufficient stability. This arrangement also enable in particular to use known
19 secondary extruders and to provide them with a respective extension piece so
20 that this embodiment can be realized in a comparably cost-efficient manner.

21
22 Finally, the invention proposes a process for charging a main extruder of
23 an injection molding device with a melt from a secondary extruder, with the melt

1 being filled in the main extruder through a feed channel in a hot runner which is
2 connected to the main extruder, on the one hand, and terminates in a mold, on
3 the other hand, whereby the injection process is so controlled as to leave a sprue
4 of solidified or solidifying workpiece in the hot runner between mold and the
5 location where the feed channel terminates in the hot runner, until the main
6 extruder is filled with the melt.

7
8 This ensures that melt does not flow inadvertently from the secondary
9 extruder in the direction of the workpiece, but reaches the main extruder. As
10 soon as the main extruder is accordingly filled, the workpiece can be ejected.

11
12 As a consequence of the above-described process, the use of a valve in
13 the hot runner can be omitted.

14
15 Advantageously, the sprue extends to immediately the area where the
16 feed channel terminates in the hot runner.

17
18 The process according to the invention and various exemplified
19 embodiments for applying the process according to the invention are explained in
20 more detail with reference to the drawing, in which:

21
22 FIG. 1 is a schematic three-dimensional view of an injection
23 molding device with mold;

FIG. 2 is a sectional cutaway view from FIG. 1;

FIG. 3 is a schematic sectional view of an alternative embodiment of an injection molding device;

FIG. 4 is a sectional view through a cap component;

FIG. 5 is a detail, on an enlarged scale, of FIG. 4;

FIG. 6 is a sectional view through a further cap component;

FIG. 7 is a sectional view through a caster component;

FIG. 8 is a sectional view through a part of the caster component according to FIG. 7, illustrating an embodiment with profile;

FIG. 9 is a sectional cutaway view of the caster component according to Fig. 7, illustrating an interlocking tire connection;

FIG. 10 is a sectional cutaway view of the caster component according to Fig. 7, illustrating a gas-filled tire component;

FIG. 11 is a sectional cutaway view of the caster component

1 according to Fig. 7, illustrating a tire component injected from the direction of the
2 hub;

3
4 FIG. 12 is a sectional view through a caster component with ball
5 caster;

6
7 FIG. 13 is a sectional view through a handle;

8
9 FIG. 14 is an illustration of a brush handle;

10
11 FIG. 15 is a sectional view through a housing having an upper part
12 accommodating a schematically depicted seal and a lower part accommodating a
13 schematically depicted seal in the cap part and cable feedthrough;

14
15 FIG. 16 is a sectional view through a screwed cable connection;

16
17 FIG. 17 is an illustration of a first embodiment of a bottle closure;

18
19 FIG. 18 is a sectional view through another embodiment of a bottle
20 closure;

21
22 FIG. 19 is an injection molding device with mold;

FIG. 20 is a cutaway view from FIG. 19 with a hot runner for hot runner injection molding;

FIG. 21 is a schematic illustration of a further injection molding device;

FIG. 22 is a perspective illustration of a hot runner block with adjustment nozzle as control unit;

FIG. 23 is a sectional view through the adjustment nozzle according to FIG. 4;

FIG. 24 is a schematic sectional view through a further control unit;

FIG. 25 is a schematic illustration of a pivoting nozzle serving as control unit; and

FIG. 26 is a schematic illustration of a further injection molding device.

The injection molding device 1 shown in FIG. 1 includes a nozzle 2 which is connected to a mold 3. Disposed on the other side of the nozzle are two secondary extruders 4 and 5 which are placed upon the main extruder 6. Both

secondary extruders have feed hoppers 7 and 8, and the main extruder has a feed hopper 9.

The mold 3 has a first inlet 10 for plasticized components and a second inlet 11 for a gas to form a hollow in the injection molded part. In addition, a slide gate 12 is provided in the mold 3. This slide gate 12 ensures that initially only a partial area of the wall surface of the hollow in the mold cavity is wetted with plasticized material, and that a remaining area of the wall surface of the hollow is only wetted with plasticized material after the slide gate 12 has been drawn. Thus, the cavity of the mold is subdivided into a partial area and a remaining area, with the remaining area being cleared only after the slide gate 12 has been drawn.

FIG. 2 is a sectional view of that part of the injection molding device 1 which is adjacent to the nozzle 2. Adjoining the nozzle 2 is a partial area with a first plasticized material 13 which is supplied via the feed hopper 7 and the secondary extruder 4. Then follows a further area which is supplied with a second plasticized material 14 via the hopper 8 and the secondary extruder 5. The remaining area of the injection molding device 1 is filled with a third plasticized material 15 supplied via the funnel 9 and conveyed in the main extruder 6 by means of a screw 16.

This enables to sequentially introduce different plasticized materials 13,

14, 15, into the mold 3 via the nozzle 2. Preferably, the slide gate 12 is drawn when changing from one material to the other material, to wet a partial area of the wall surface of the hollow of the mold with another plasticized material.

FIG. 3 shows another injection molding device according to the invention. Here, extruders 21, 22 and 23, 24 are arranged respectively on two sides of a mold 20. The extruders 21 and 22 feed plasticizeable material to a channel 25 which leads to an opening 26 in the mold 20, and the extruders 23 and 24 feed plasticized material to a channel 27 which leads to an opening 28 in the mold 20.

To operate the device, plasticized material can either be initially fed to the cavity 29 of the mold 20 by the extruder 21, whereupon subsequently another plasticized material is fed to the cavity 29 by the extruder 22. Alternatively, it is also possible to initially push plasticized material into extruder 22 by means of extruder 21, whereupon thereafter the extruder 22 feeds first the plasticized material originating from extruder 21 into the cavity 29, and subsequently the extruder 22 conveys readied plasticized material. Of course, the same process variants are also possible with extruders 23 and 24, although the process according to the invention can be carried out also solely with the extruders 21 and 22.

The channel 30 connects the extruders 23 and 24 with the extruders 21 and 22, optionally assisted by an interposed pump 31, so that it is possible to

1 feed four different plasticized materials at the opening 26 or the opening 28 in
2 succession into the cavity 29 of the mold 20. For sake of clarity, the respectively
3 required slide gates have not been illustrated. However, the artisan readily
4 recognizes that the device according to FIG. 3 enables introduction of four
5 different materials through one opening 26 or 28 into the cavity 29, and that the
6 device allows various process control methods as a result of installed slide gates.

7
8 Thus, it is, for example, possible to produce with a device according to
9 FIG. 1 or 3, the cap component 40 shown in Fig. 4. Hereby, a harder material 42
10 is initially injected at sprue 41 into an injection mold and hardens at the walls of
11 the mold. Subsequently, a slide gate is drawn to clear an opening in the
12 areas 43, 44 so that softer material 45 conveyed at sprue 41 flows in the cavity of
13 the mold up to the space cleared by the slide gate, to form a protruding seal 46.

14
15 Thus, the cap 40 has an envelope of harder material 42 with a subjacent
16 softer material 45 which is visible only in the marginal area of the cap 40 as
17 ring-shaped seal 46.

18
19 The sprue area, shown on an enlarged scale in FIG. 5, depicts the harder
20 plasticized material 42, which hardens at the wall surfaces of the cavity, and the
21 softer material 45 conveyed at point 41 flows into the mold in the central area
22 between the wall surfaces of the cavity.

1 FIG. 6 shows an alternative embodiment for making a cap by the process
2 according to the invention. The cap component 50 shown there includes an
3 arched cap part 51 which is initially injection-molded via a channel 52 from the
4 direction of the mold inlet 53. Subsequently, the slide gate 54 is so repositioned
5 that softer material flowing from the opening 53 enters a sealing area 57 cleared
6 by a slide gate via the channels 55 and 56, to form a ring-shaped seal 58 which
7 is fixedly secured to the arched cap component 51 of harder material.

8
9 Instead of, or in addition to, the use of a slide gate, a shoulder 59
10 (compare FIG. 4) may be provided in the mold at the transition point between the
11 materials, to ensure that the first plasticized material flows only up to this
12 shoulder, and only the second plasticized material is able to flow beyond this
13 shoulder. Such a shoulder 59 extends in FIG. 4 transversely to the flow direction,
14 with a further shoulder 60 arranged in opposite disposition. As a result, the hard
15 component 42 flows only to the shoulders 59 and 60 and hardens at the margin
16 of the mold. The subsequently flowing material 45 is no longer retarded by the
17 shoulders 59 and 60 because the external plasticized material 52 has already
18 hardened up to the inner edge of the shoulder, so that the subsequently flowing
19 material 45 flows beyond the shoulder and wets the remaining area of the wall
20 surface of the hollow.

21
22 FIGS. 7 to 11 show a caster component 70 with various configurations of
23 a radially outwardly positioned tire 71 to 75. In its basic version, the caster

1 component 70 includes a hub 76 and a radially adjacent tire 71. The mold
2 provided for injection molding this component has an inlet 77, which leads to a
3 channel 78, to injection-mold the hub part 76 from a harder material.
4 Subsequently, a slide gate 79, arranged between the inlet 77 and the channel 78,
5 is so repositioned that softer material streams via the channel 80 into the radially
6 outwardly located region of the hub 76, to form a tire 71.

7
8 The modified embodiment according to FIG. 8 provides a profile in the
9 tire 72. According to FIG. 9, the tire 73 is connected to the hub component 76 by
10 an interlocking connection 81. FIG. 10 shows the inclusion of a gas into the tire
11 part to achieve a "balloon effect" by means of an air bubble 82. Lastly, the
12 exemplified embodiment according to FIG. 11 shows an alternative way of
13 making the tire by injecting the softer tire component via the channel 78
14 subsequent to injecting the harder component, so that, like in the case of the cap
15 component according to FIG. 4, the softer component flows through the center of
16 the harder component and forms a tire 75 radially on the outside. Also in this
17 case, either a slide gate, which clears a remaining area of the cavity, or a
18 shoulder, which inhibits the flow of the first component, can be applied.

19
20 FIG. 12 shows a further caster component, also called a ball caster 90.
21 Hereby, a hard component is initially injected into the mold via an annular
22 sprue 91, and subsequently a soft component is injected via the sprues 92
23 and 93. Like the cap component according to FIG. 4, this component, too, can be

1 made with two different materials injected in succession at sprue 91. The
2 hardness of the soft component 94 can be adjusted by admixing elastomeric
3 recycling particles.

4
5 FIG. 13 shows a handle 100 which includes a handle body 101 and a
6 handle shell 102, with a gas bubble 103 preferably provided in the handle body.
7 The handle body is made from a harder material through injection via the
8 inlet 104 and the handle shell is made from a foamed material through injection
9 via the inlet 105. Optionally, soft components, for example for door handles or as
10 handbrake levers as well as for pedals, can be injected from inside.

11
12 FIG. 14 shows a brush handle 110 which is made by injecting initially a
13 soft component 111 via the sprue 112 and subsequently by injecting a hard
14 component 114 via the sprue 113. Of course, the various materials 111 and 114,
15 like in the other exemplified embodiments, may also have, additionally or
16 alternatively, various colors or include plasticizeable materials of various
17 properties in some other way. In particular, any kind of handles, flatware, for
18 example for camping with soft handle, designer flatware, toothbrushes or tool
19 handles, may be made through this process. Through combination with a gas
20 bubble, also two-component hollow parts can, for example, be made, especially
21 handles or the like.

22
23 The manufacture of a housing 120, as shown in FIG. 15, is a further

1 frequent application of the process described herein. As shown by the schematic
2 illustration of FIG. 15, this housing has in the upper part of the drawing a
3 seal 121 which is located in the housing part, and in the lower part of the figure a
4 seal 123 which is arranged in a matching cap part 122 and interacts with a
5 complementarily shaped counterpart 124 in the housing 120. This housing can
6 be made analogous to the previously described cap according to the process
7 shown in FIGS. 4 and 6. An advantageous configuration of the housing shows a
8 cable feedthrough 125 which has a ring 126 of a softer plastic material.

9
10 FIG. 16 shows a screwed cable connection 130 with a claw-shaped strain
11 relief 131 and a seal 132. In this embodiment, a harder component 134 is initially
12 injected through mold inlet 133 to form the body of the screwed cable
13 connection 130 and the claws of the strain relief 131. Subsequently, the slide
14 gate 135 is so repositioned that in addition to the central channel 136, two further
15 channels 137 and 138 are cleared so that subsequently flowing softer material
16 can flow into a region cleared by a slide gate (not shown), to form the seal 132.
17 At the same time, a partial stream of the softer material in the central
18 channel 136 flows to the strain relief 131 to form also there a body 139 of softer
19 material.

20
21 While in the upper part of FIG. 16, the claws of the strain relief 131 are
22 shown in their uncompressed state, the lower part of FIG. 16 shows how the
23 claws of the strain relief 131 are compressed by means of a screwed-on

1 clamping nut 140.

2
3 It will be appreciated that a number of electric articles or auxiliary electric
4 articles can be made in this fashion.

5
6 FIG. 17 shows a bottle closure 150 as a further embodiment. This bottle
7 closure is made from a harder component 151, which forms the base body, and a
8 softer component 152, which protrudes in the form of a ring in a certain region
9 and acts as a seal. A gas bubble 153 is provided within the harder
10 component 151 to save material and to attain a higher flexibility of the bottle
11 closure. The closure may also be constructed of solid configuration.

12
13 FIG. 18 shows a further bottle closure 160. This bottle closure includes a
14 hard inner part 161 which is surrounded by a softer material 162, whereby it is
15 also possible to reverse the type of materials. The inner part 161 includes
16 ribs 165 which extend, preferably, from a central axis 163 to a ring body 164.

17
18 The process according to the invention can be used for numerous further
19 applications such as wheels made of hard and soft components, to children's
20 toys made of differently colored components, joints of hard and soft components
21 up to caps having opaque and transparent zones. Further examples include:
22 screwdriver handles, hangers with anti-slip edges, shock absorbers, buffers,
23 silent blocs, furniture hardware, buttons or shoe soles. Also parts can, for

1 example, be made of which at least one material component are antistick or
2 hydrophobic. This component is then quasi self-cleaning and could be used, for
3 example, for shoe soles, in particular shoe soles with cleats. Important areas of
4 application include moreover transport belts, transport drums and transport
5 rollers.

6
7 FIGS. 19 and 20 show the use of a mold with a special hot runner. When
8 injecting two different materials 170, 171 with an injection unit 172 into a
9 mold 173, several materials 170, 171 are fed in succession into the mold 173.
10 Thereby, an outer ring made from the first component 170 forms in the hot runner
11 and accommodates as a core the further component 172. After conclusion of the
12 injection process with the component 171, it is however necessary to again feed
13 new component 170 which, normally, pushes the remaining residue of the
14 second component 171 in the hot runner 174 as contamination into the cavity.

15
16 FIG. 20 shows an overflow 175 and a slide gate 176 in the hot runner 174
17 to avoid such contamination. The slide gate 176 enables to press the remainder
18 of the second component 171 with subsequently fed first component 170 into the
19 overflow 175 and to clear the cavity 177 only when first material is again provided
20 at the slide gate 176. Thus, the use of a sprue rod is no longer necessary.

21
22 FIG. 21 illustrates an injection molding device which includes an injection
23 unit with an injection piston 201 for injecting melt from a melt compartment 202.

Two extruders 203 and 204 fill the melt compartment 202 with melt. The injection piston 201 is driven by an injection cylinder 205. Particularly fine precision components can be made with such an arrangement. This arrangement is especially suitable for micro injection molding with two different starting materials.

The connection between the extruders 203 and 204 may be ensured, on the one hand, via valves. It is, however, also possible to ensure a desired filling of the melt compartment 202 through appropriate selection and control of the melt streams flowing during filling.

FIG. 22 shows a hot runner block 230 which interacts with a particular adjustment nozzle 231. This adjustment nozzle 231 is secured to a secondary extruder 263 by a flange. In this manner, the adjustment nozzle 231 can very easily be positioned. When adjusting the adjustment nozzle, in particular the distance of the nozzle end will not change, as is the case with threadably engaged conventional adjustment nozzles.

The hot runner block 230 has a through channel 232 and a round central opening 233 which intersects the channel 232 for receiving the adjustment nozzle 231. This nozzle 231 has a bore 234 which extends transversely to the nozzle axis, with the bore corresponding to the diameter of the channel 232 and aligned with the channel 232 through counterboring the adjustment nozzle in the opening 233 of the hot runner block 230.

1 Above the bore 234, the adjustment nozzle 231 is provided with a
2 L-shaped bore 235 which should also be aligned with the channel 232 and then
3 connects the secondary extruder 236 with the channel 232 to convey
4 plasticizeable material from the secondary extruder 236 through the L-shaped
5 channel 235 into the channel 232.

6
7 The channel 232 is further in communication with a main extruder 237.

8
9 The adjustment nozzle 231 thus operates as control unit to provide a flow
10 path between the main extruder 237 and the secondary extruder 236 and
11 workpiece. It will be understood that such an adjustment nozzle 231 is also
12 advantageous for other control units.

13
14 Furthermore, the flange-mounting can advantageously be used,
15 regardless of other features of the adjustment nozzle 231, for any kind of nozzles
16 which should be precisely adjusted.

17
18 Another control unit is shown in FIG. 24 and includes a hot runner 241 for
19 conducting melt from a main extruder to a mold nest (as indicated by the arrow
20 246). Branching off from this hot runner 241 is a partial channel 242 which can
21 be connected, depending on need, with a feed channel 243 of a secondary
22 extruder. This is attained by moving a sleeve, which surrounds the hot runner
23 and accommodates the feed channel 243, along the hot runner 241. Through this

1 movement, the feed channel 243 may selectively be aligned with the partial
2 channel 242.

3
4 To prevent melt from migrating in the direction of the mold nest during
5 filling of the main extruder by the secondary extruder, a pressure valve is
6 positioned in the hot runner 241 immediately behind the location where the
7 partial channel 242 branches off. The pressure valve is so dimensioned as to
8 close at pressure applied by the secondary extruder and to open at a pressure
9 applied by the main extruder.

10
11 Instead of the pressure valve 245, the injection molding process may also
12 be controlled in such a manner that a sprue extends from the mold nest and
13 remains in the hot runner 241 which extends to this previously described
14 location. The sprue ensures that the melt does not flow in the direction of the
15 mold nest. Only when the main extruder is filled in a desired manner will the
16 workpiece be ejected with the sprue so that the hot runner 241 is cleared again.

17
18 A further control unit is shown in FIG. 25 and provided in the form of a
19 pivoting nozzle 250 having an inlet 251 and an outlet 252 which are
20 interconnected by a channel 253. The pivoting nozzle 250 is swingable about an
21 axis 254 and secured by means of a fastening flange 255 to a tie rod 246 of the
22 main extruder 257.

1 In the charging position (shown in FIG. 25), the inlet 252 points to the
2 injection nozzle of the main extruder 257, while the inlet 251 points to a
3 secondary extruder 258. In this position, the main extruder 257 and the
4 secondary extruder 258 can be brought into contact with the inlet 251 and the
5 outlet 252, respectively, and melt can be filled into the main extruder 257.

6
7 After charging the main extruder in a desired manner, the pivoting
8 nozzle 250 is tilted upwards in the direction of the arrow, so that the path for the
9 main extruder 257 is cleared and the latter can travel into its injection position.

10
11 According to another embodiment, the secondary extruder 258 may be
12 securely fixed to the pivoting nozzle 250 and swung in unison with the latter.

13
14 As can be seen from FIGS. 24 and 25, the secondary extruder and the
15 main extruder are arranged at an acute angle relative to one another or arranged
16 in a V-shaped disposition. This enables a positioning of the control unit 240
17 and 250, respectively, in immediate proximity of the workpiece, so that the
18 distances to be traveled by the main extruder can be minimized. As a result, the
19 injection process can be carried out at increased speed.

20
21 FIG. 26 depicts a further possibility of increasing the working speed of an
22 injection device which includes a main extruder having a nozzle 301 traversing a
23 nozzle plate 302 as well as a portion of an adapter plate 303 through an injection

1 opening 304 to reach its injection position. The nozzle plate 302 denotes hereby
2 an end of the mold space on the main extruder side, whereas the adapter
3 plate 303 is a part arranged on the nozzle plate 302 for conforming to various
4 molds or the like.

5
6 Provided in the adapter plate 303 is an opening 305 which terminates in
7 the injection opening 304. Extending through the opening 305 is an extension
8 piece 306 which leads from a secondary extruder to an outlet 307. Through
9 moving the secondary extruder, the outlet 307 can be aligned with the injection
10 opening 304 so that the main extruder can be charged from the secondary
11 extruder when the nozzle 301 bears against the outlet 307.

12
13 For reasons of stability, the secondary extruder has an end which faces
14 away from the outlet 307 and includes a lug 308 for engagement in a respective
15 recess 309 of the adapter plate 303. For cleaning purposes, the recess 309 may
16 be extended out of the adapter plate 303 so as to allow a discharge of excess
17 melt.

18
19 As immediately evident, such an arrangement results in a minimized path
20 to be traveled by the nozzle 301, when an adapter plate is provided in the mold
21 space.

Standard components may be used as extension piece 306 so that this embodiment is further especially cost-efficient. To prevent an escape of melt, needle shut-offs may be provided at the outlet 307 and the nozzle 301.

Through the above-described arrangements and processes, especially pipes with a connection sleeve, hoses with fastening elements, brackets or plug connectors, pipes with flexible intermediate pieces or clutch pedals or other pedals, including lever gears and bar linkages with a soft element at the pedal pad, can also be made.

All this can be carried out in a single injection operation, thus significantly reducing the process time.

In practical application, the changeover from a first component to a further component, and, optionally, to a third, fourth etc. component, requires considerable experience, because the timing has to be exactly right. In order to ascertain the correct moment, sensors can be provided in the injection molding device and in particular in the mold or in an ejection bore for monitoring through pressure, temperature or ultrasound the filling of the cavity with the various plasticized materials. For better process monitoring, a pause can be introduced between the supply of different plasticized materials. In addition, the control of movement of the screw, i.e. the distance of material conveyed by the screw, can be used directly for controlling the slide gates. Instead of the distance, it is also

- 1 possible to measure the time elapsed from commencement of the injection
- 2 procedure, to determine the correct moment for control of the slide gate. Finally,
- 3 it is also possible to use the interior pressure of the mold as a parameter for the
- 4 slide gate control.

CLAIMS

1. Process for injection molding of injection molded parts from plasticizeable material, including injecting a first plasticized material into the hollow of an injection mold and subsequently injecting another plasticized material into the hollow, characterized in that the first plasticized material is so introduced into the hollow as to wet only a partial area of the wall surface of the hollow, and that subsequently the other plasticized material is so introduced into the hollow as to wet at least a part of the remaining area of the wall surface of the hollow.

2. Process according to claim 1, characterized in that the first plasticized material and at least one other plasticized material are injected into the hollow through the same opening.

3. Process according to one of the preceding claims, characterized in that the first material is injected into the injection mold to such an extent that after injection of the other material, the first material extends to a shoulder in the hollow between the partial area and the remaining area.

4. Process according to one of the preceding claims, characterized in that after injection of the first material, a slide gate is moved to clear at least a part of the remaining area.

1 5. Process according to claim 4, characterized in that the slide gate clears a
2 channel leading to a partial area of the hollow in the injection mold.

1 6. Process according to claim 4, characterized in that the slide gate directly
2 clears a partial area of the hollow in the injection mold.

1 7. Process according to one of the preceding claims, characterized in that
2 during the injection molding operation a gas space is formed in the injection
3 mold.

1 8. Process according to one of the preceding claims, characterized in that one
2 plasticized material is a relatively soft or rubber-like material, and at least
3 one other plasticized material is a relatively hard material.

1 9. Process according to one of the preceding claims, characterized in that the
2 plasticized materials exhibit at least two different colors or are transparent.

1 10. Process according to one of the preceding claims, characterized in that at
2 least one plasticized material contains gas pockets.

1 11. Process according to one of the preceding claims, characterized in that at
2 least one plasticized material contains pockets of another component.

1 12. Injection mold, characterized in that it comprises a sensor arranged at the
2 transition between the partial area and the remaining area of the wall
3 surface of the hollow in the injection mold.

1 13. Injection mold, in particular according to claim 12, characterized in that it
2 comprises a shoulder arranged at the transition between the partial area
3 and the remaining area of the wall surface of the hollow in the injection
4 mold.

1 14. Injection mold, in particular according to claim 12 or 13, characterized in
2 that it comprises a hot runner with a by-pass device which enables
3 plasticized material, streaming to the hollow, to flow into an overflow.

1 15. Injection molding device with a plasticizer unit and an injection unit,
2 characterized in that it comprises at least two secondary extruders which
3 are arranged between screw tip and nozzle tip.

1 16. Injection molding device having at least one injection unit which includes an
2 injection piston (201) for injecting melt from a melt compartment, and at
3 least two extruders (203, 204) connected to this melt compartment.

1 17. Injection molding device having a main extruder (237, 257) which includes a
2 melt compartment from which a nozzle extends via a hot runner (241), and
3 a secondary extruder (236, 258), characterized in that the melt
4 compartment is connected via a control device (230, 240) to a second
5 channel which is connected with the secondary extruder (236, 258) and
6 leads to the melt compartment, with the control device being coupled with
7 the movement of the secondary extruder.

1 18. Injection molding device according to claim 17, characterized in that the
2 control unit (230, 240) is rigidly connected with the secondary
3 extruder (236).

1 19. Injection molding device according to claim 17 or 18, characterized in that
2 the control unit (230) includes an adjustment nozzle which bears upon a
3 surface, preferably of a secondary extruder, and is secured to a flange.

1 20. Injection molding device according to one of the claims 17 to 19,
2 characterized in that the hot runner (241) includes a pressure-dependent
3 valve (245).

1 21. Injection molding device according to one of the claims 17 to 20,
2 characterized in that the control unit (230, 240) includes two partial
3 channels (234, 235; 241, 242, 243) which, depending on the position of the
4 control unit, open or close the hot runner or a feed channel from the
5 secondary extruder.

1 22. Injection molding device according to claim 21, characterized in that the
2 control unit (230) includes a partial runner block (231) which accommodates
3 the partial channels (234, 235) and is guided in a block guide (233).

1 23. Injection molding device comprising a main extruder (257) movable along a
2 path between an injection position and an idle position, and a secondary
3 extruder (258), characterized by a control unit (250) which is arranged
4 between the injection position and the idle position and includes a
5 channel (253) with an inlet (251) and an outlet (252) and which is swingable
6 between a charging position and release position, wherein the inlet (251)
7 points to the main extruder (257) in the charging position, and the
8 outlet (252) points to the main extruder (257), and wherein the path is
9 cleared for the main extruder (257) in the release position.

1 24. Injection molding device according to claim 23, characterized in that the
2 inlet (251) and the outlet (252) define an acute angle relative to one
3 another.



1 25. Injection molding device comprising a main extruder movable along a path
2 between an injection position and an idle position, and having a
3 nozzle (301) for projecting in its injection position through a nozzle
4 plate (302) and at least a portion of an adapter plate (303) through an
5 injection opening (304), and a secondary extruder which is shiftable
6 between a charging position and a release position, wherein in the release
7 position the path of the main extruder is cleared and in the charging position
8 an outlet (307) of the secondary extruder points to the nozzle (301) of the
9 main extruder, characterized in that the outlet (307) is arranged in an
10 opening (305) of the adapter plate (303) which terminates in the injection
11 opening (304).

1 26. Injection molding device according to claim 25, characterized in that the
2 secondary extruder is supported on its side of the outlet, at least in its
3 charging position, by a force applied by the main extruder.

1 27. Method of charging a main extruder of an injection molding device with a melt
2 from a secondary extruder, comprising filling the melt into the main extruder
3 via a feed channel in a hot runner which, on the one hand, is connected with
4 the main extruder and, on the other hand, leads to a mold, and so controlling
5 the injection process that in the hot runner between mold and the location at
6 which the feed channel terminates in the hot runner, a sprue of a solidified or
7 solidifying workpiece remains, until the main extruder is filled with melt.

ABSTRACT

In the process according to the invention a first plasticized material is injected into the hollow in an injection mold and subsequently another plasticized material is injected into this hollow. The process is characterized in that the first plasticized material is so introduced into the hollow as to wet only a partial area of the wall surface of the hollow; and that subsequently the other plasticized material is so introduced into the hollow as to wet at least a part of the remaining area of the wall surface of the hollow. The process according to the invention permits to use simple injection molding devices to make injection molded parts from different materials.














Fig. 3








Fig. 12







Fig. 13






Fig. 17




Fig. 18




Fig. 19





Fig. 20

Fig. 21






Fig. 23






Fig. 22

Fig. 24








Fig. 26

Declaration and Power of Attorney for Patent Application

Erklärung für Patentanmeldungen mit Vollmacht

German Language Declaration

Als nachstehend benannter Erfinder erkläre ich hiermit an Eides Statt:

daß mein Wohnsitz, meine Postanschrift, und meine Staatsangehörigkeit den im Nachstehenden nach meinem Namen aufgeführten Angaben entsprechen,

daß ich, nach bestem Wissen, der ursprüngliche, erste und alleinige Erfinder (falls nachstehend nur ein Name angegeben ist) oder ein ursprünglicher, erster und Miterfinder (falls nachstehend mehrere Namen aufgeführt sind) des Gegenstandes bin, für den dieser Antrag gestellt wird und für den ein Patent beantragt wird für die Erfindung mit dem Titel:

VERFAHREN ZUM SPRITZGIESSEN, SPRITZGIESSFORM UND SPRITZGIESSVORRICHTUNG SOWIE VERFAHREN ZUM BEFÜLLEN EINES HAUPTEXTRUDERS AUS EINEM NEBENEXTRUDER

deren Beschreibung
(zutreffendes ankreuzen)

- ☐ hier beigefügt ist.
☒ wurde angemeldet am 21. August 1998 unter der U.S.-Anmeldungs Nr. oder unter der Internationalen Anmeldenummer im Rahmen des Vertrags über die Zusammenarbeit auf dem Gebiet des Patentwesens (PCT) PCT/DE98/02449 und am _____ abgeändert (falls zutreffend).

Ich bestätige hiermit, daß ich den Inhalt der obigen Patentanmeldung einschliesslich der Ansprüche durchgesehen und verstanden habe, die eventuell durch einen Zusatzantrag, wie oben erwähnt, abgeändert wurde.

Ich erkenne meine Pflicht zur Offenbarung irgendwelcher Informationen an, die für die Prüfung der vorliegenden Anmeldung in Einklang mit Titel 37, Code of Federal Regulations, §1.56 von Belang sind.

Ich beanspruche hiermit ausländische Prioritätsvorteile gemäss Titel 35, US-Code, §119(a)-(d), bzw. §365(b) aller unten angegebenen Auslandsanmeldungen für ein Patent oder Erfinderurkunden, oder §365(a) aller PCT internationalen Anmeldungen, welche wenigstens ein Land ausser den Vereinigten Staaten von Amerika benennen, und habe nachstehend durch ankreuzen sämtliche Auslandsanmeldungen für Patente oder Erfinderurkunden oder PCT internationale Anmeldungen angegeben, deren Anmeldetag dem der Anmeldung, für welche Priorität beansprucht wird, vorangeht.

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

METHOD FOR INJECTION MOLDING, INJECTION MOLD, INJECTION MOLDING DEVICE AND METHOD FOR FILLING A MAIN EXTRUDER FROM A SECONDARY EXTRUDER

the specification of which
(check one)

- ☐ is attached hereto
☒ was filed on 21 August 1998 as United States Application Number or PCT International Application Number PCT/DE98/02449 and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, §119(a)-(d) or §365(b) of any foreign application(s) for patent or inventor's certificate, or §365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

1 of 3

Prior Foreign Applications
(Frühere ausländische Anmeldungen)

Priority Claimed?
Priorität beansprucht?

197 36 371.7 Germany 21/August/1997
(Number) (Country) (Day/Month/Year Filed)
(Nummer) (Land) (Tag/Monat/Jahr eingereicht)

198 08 145.6 Germany 27/February/1998
(Number) (Country) (Day/Month/Year Filed)
(Nummer) (Land) (Tag/Monat/Jahr eingereicht)

[X] []
Yes No
Ja Nein

[X] []
Yes No
Ja Nein

Ich beanspruche hiermit gemäss Titel 35, US-Code, §119(e), den Vorzug aller unten aufgeführten US-Hilfsanmeldungen

I hereby claim the benefit under Title 35, United States Code, §119(e) of any United States provisional application(s) below

60/076.472 2/March/1998
(Application No. / Anmeldendr.) (Filing Date / Anmeldedatum)

(Application No. / Anmeldendr.) (Filing Date / Anmeldedatum)

Ich beanspruche hiermit gemäss Titel 35, US-Code, §120, den Vorzug aller unten aufgeführten US-Patentanmeldungen bzw. §365(c) aller PCT internationalen Anmeldungen, welche die Vereinigten Staaten von Amerika benennen, und erkenne, insofern der Gegenstand eines jeden früheren Anspruchs dieser Patentanmeldung, bzw. PCT internationalen Anmeldung in einer gemäß dem ersten Absatz von Titel 35, US-Code §112 vorgeschriebenen Art und Weise offenbart wurde, meine Pflicht zur Offenbarung jeglicher Informationen an, die zur Prüfung der Patentfähigkeit in Einklang mit Titel 37, Code of Federal Regulations, §1.56 von Belang sind und im Zeitraum zwischen dem Anmeldedatum der früheren Patentanmeldung und dem nationalen oder im Rahmen des Vertrags über die Zusammenarbeit auf dem Gebiet des Patentwesens (PCT) gültigen internationalen Anmeldedatum bekannt geworden sind.

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s), or §365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

(Appl. No.) (Filing Date)
(Anmeldendr.) (Anmeldedatum)

(Status)
(patentiert, anhängig
aufgegeben)

(Status)
(patented, pending
abandoned)

(Appl. No.) (Filing Date)
(Anmeldendr.) (Anmeldedatum)

(Status)
(patentiert, anhängig
aufgegeben)

(Status)
(patented, pending
abandoned)

Ich erkläre hiermit, daß alle von mir in der vorliegenden Erklärung gemachten Angaben nach meinem besten Wissen und Gewissen der vollen Wahrheit entsprechen, und daß ich diese eidesstattliche Erklärung in Kenntnis dessen abgebe, daß wissentlich und vorsätzlich falsche Angaben gemäss §. 1001, Titel 18 US-Code strafbar sind und mit Geldstrafe und/oder Gefängnis bestraft werden können, und daß derartig wissentlich und vorsätzlich falsche Angaben die Rechtswirksamkeit der vorliegenden Patentanmeldung oder eines darauf erteilten Patentbeschlusses gefährden können.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under §1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

VERTRETUNGSVOLLMACHT: Als benannter Erfinder beauftrage ich hiermit den nachstehend benannten Patentanwalt (oder die nachstehend benannten Patentanwälte) und/oder Vertreter mit der Verfolgung der vorliegenden Patentanmeldung sowie mit der Abwicklung aller damit verbundenen Geschäfte vor dem US-Patent-und Warenzeichenamt:

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:

HENRY M. FEIEREISEN
Reg. No. 31,084

Telefongespräche bitte richten an:
(Name und Telefonnummer)

Direct telephone calls to:
(Name and telephone number)

HENRY M. FEIEREISEN
(212) 244-5500

Postanschrift



020151

PATENT 006111 MARK OFFICE

CUSTOMER NO. 020151
Henry M. Feierelsen
350 Fifth Avenue, Suite 3220
New York, N.Y. 10118

Send Correspondence to:

Voller Name des einzigen oder
ursprünglichen Erfinders

Full name of first inventor

HEINER BECKER

[Handwritten Signature]

15-03-2000

Unterschrift des Erfinders

Datum

Inventor's Signature

Date

Wohnsitz

Aachen / Germany

[Handwritten Mark]

Residence

Staatsangehörigkeit

Germany

Citizenship

Postanschrift

Reumont Strasse 34
52064 Aachen
Germany

Post Office Address

3 of 3